

CAF[®] 33**Industrial range****Description**

CAF 33 is a room temperature curing silicone elastomer:

- ACETIC.
- NON FLOWING.
- BLACK, WHITE, TRANSLUCENT.

Examples of applications

This product is more specifically intended for industrial customers who use it for bonding/sealing in various applications:

- Automotive:
 - sealing on engines,
 - bonding/sealing of sunroofs.
- Domestic appliances:
 - bonding of oven door brackets,
 - sealing of washing machine tanks.
- Aeronautic:
 - miscellaneous bonding applications.
- Industry:
 - sealing of molding compartments,
 - bonding of HCR silicones,
 - sealing of industrial rotary machines (pumps, turbines, compressors).

Advantages

- Resists very high temperatures.
- Good dielectric properties.
- Adhesion to many surfaces.
- High resistance to chemical agents.
- Resistance to water and humidity.

Characteristics**1. Processing/Curing**

Processing is particularly easy since the product is delivered ready to use. Application can be carried out manually or using robotize application equipment.

The **CAF 33** bead is applied onto one of the two joint surfaces. Assembly must be carried out before the product has formed a skin.

It is recommended not to exert an immediate strain on the assembly.

Curing

Curing of **CAF 33** starts as soon as the product comes into contact with atmospheric humidity.

Skin formation time*, min.....	6
Cure rate of 2 mm thickness*, h.....	6
Cured thickness after 24 h*, mm.....	4,3

*Temperature 23 °C - relative humidity 50 %

The cure rate increases with temperature and hygrometry.

Comment: it is recommended to apply the product to clean, dry surfaces.

Examples: curing time for 2 mm thickness, according to temperature and hygrometry:

Temperature	25 °C			50 °C			90 °C		110 °C	103 °C
Relative humidity in %	25	50	70	25	50	70	25	50	70	20
2 mm cured thickness	14 h	6 h	4 h	4 h	2 h	2 h	50 min	30 min	17 min	16 min

2. Properties before curing

Appearancenon flowing paste
 Colorsblack, white, translucent
 Cure type..... acetic
 Flowability, in mm ≤ 2
 (Standard BOEING S 7502, NMRPS 459)
 Extrusion, g/min 50
 (Standard NMRPS 495 A, 3 mm / 3 bars)
 Specific gravity at 25 °C 1.04
 (Standards ISO R 1183, DIN 53479, NMRPS703)

3. Properties after curing

3.1. *Specific gravity at 25 °C*..... 1.05
 (Standards ISO 2781, ASTM D 297, BS 903 Part A1)
 3.2. *Mechanical properties after 7 days*
 Shore A hardness 25
 (Standards ISO R 868, DIN 53505, ASTM D 2240
 BS 903 Part A7, NFT 46003, NMRPS 471)
 Modulus at 100 % elongation, MPa 0.6
 (Standard ISO R 37 (H2), DIN 53504, ASTM D 412
 BS 903 Part A2, NFT 46002 (H2), NMRPS 470)
 Tensile strength, MPa 2.5
 (Standards ISO R 37 (H2), DIN 53504, ASTM D 412
 BS 903 Part A2, NFT 46002 (H2), NMRPS 470)
 Elongation at break, % 500
 (Standards ISO R 37 (H2), DIN 53504, ASTM D 412
 BS 903 Part A2, NFT 46002 (H2), NMRPS 470)
 Tear strength, kN/m 5.4
 (Standards ASTM D 624 specimen 1, NMRPS 492)
 3.3. *Thermal properties or heat stability*
 Tests carried out on **CAF 33** Black
 Lower temperature limits
 Brittle point temperature..... – 65 °C
 (Measured using differential calorimetric analysis)

Upper limit in use
Maximum recommended temperature in use:

continuous + 250 °C
(on 2 mm thick film, 1000 h)

peak + 300 °C
(on 2 mm thick film, 72 h)

N.B.: *These thermal values are not absolute limits. They represent the range within which initial mechanical properties are not modified by more than 50 %.*

Furthermore, for peak uses, exposure for periods less than 72 h, allow higher maximum temperatures.

Thermal conductivity:
Tests carried out on the **CAF 33** Translucent

Thermal conductivity at 30 °C, W/m.K 0.20
(Standard NF X 10021)

Thermal conductivity at 150 °C, W/m.K 0.16
(Standard NF X 10021)

3.4. Resistance to chemicals

Tests carried out on 2 mm thick films, cured for 7 days at room temperature

Resistance to oils after 70 h immersion in the oil at 150 °C
(Standards ISO R 1817, D 471, NMRPS 525)

Oil type	Bulk Swelling (%)	Shore A hardness (points)	Modulus at 100% elongation (MPa)	Tensile strength (MPa)	Elongation at break (%)
Without oil	/	26	0.56	2.4	435
ELF Prestigrade 15 W 40	20	10	0.25	1.4	550
TEXACO 10 W 30	25	7	0.3	1.5	580
ELF Compet. SX 5 W 30	30	7	0.2	1.0	460

Resistance to anti-freeze

Tests carried out after 7 days in boiling RVI anti-freeze

Immersion in boiling RVI anti-freeze	Bulk Swelling (%)	Shore A hardness (points)	Modulus at 100% elongation (MPa)	Tensile strength (MPa)	Elongation at break (%)
Before immersion	0	26	0.58	2.2	435
After 7 days immersion	2.8	23	0.54	2.2	450

Resistance to chemicals

Tests carried out after 5 000 h immersion at room temperature

Product	Bulk Swelling (%)	Variation in tensile strength (%)	Variation in elongation at break (%)
12 % Citric acid	- 0.1	- 0.3	0
12 % Lactic acid	+ 0.3	+ 4	+ 10
2 % Hydrochloric acid	- 0.1	- 8	- 8
12 °Cl Bleach	- 1	- 20	- 15
25 % Caustic soda	- 7	- 15	- 15
25 % Sodium carbonate	- 0.2	- 12	- 10
25 % Sodium chloride	- 0.1	0	0

3.5. Compression set

Testing to measure the ability of the product to recover its initial state after compression.

(0 % = integral recovery

100 % = no elastic recovery of the product)

(Standards ASTM D 395 (specimen 1, method B), ISO R 815, NF T 46011,

NMRPS 523)

Curing time of films at room temperature	Test temperature on stack compressed to 25 % for 3 days	Compression set
3 days	150 °C	54 %

3.6. Adhesion properties

Shear strength, MPa 1.4
(Aluminum specimens AG3, joint 1 mm thick, NPRPS 748)

Type of cohesive failure, % 100

Primerless self-adhesion on..... glass, enamel, ceramics, epoxy paint, polyester

Adhesion with primer

- Stainless steel, aluminum primer PM 820

- ABS primer PP 878

CAF® 33

- Polymethyl methacrylate..... primer 131
- Composites filled to 30 % with glass fiber primer PP 878
(polyamide, polyester, polypropylene)

Adhesion to glass with immersion in various chemicals (4 months immersion)

- in isopropyl alcohol ... 100 % cohesive failure
- in ammonia solution at 20 % ditto
- in triethanol amine ditto
- in sodium chloride at 20 % ditto
- in concentrated acetic acid ditto
- in hydrochloric acid at 20 % ditto
- in nitric acid at 20 % ditto

3.7. Dielectric properties

Dielectric strength, KV/mm..... 19
(Standards NF C 26225, ASTM D 419), IEC 243)

Dielectric constant at 1MHz..... 2.8
(Standards NF C 26230, ASTM D 150, IEC 250)

Dielectric dissipation factor at 1MHz... 2×10^{-3}
(Standards NF C 26250, ASTM D 150, IEC 250)

Volume resistivity, Ω .cm..... 1×10^{14}
(Standards NF C 26215, ASTM D 257, IEC 93)

Packaging

- 100 g tubes on pallets of 1600 units (black and white).
- 310 ml cartridges on pallets of 1200 units.
- 25 kg tins on pallets of 10 units (only black).
- 210 kg drums on pallets of 4 units.

Storage and shelf life

When stored in its original unopened packaging at a temperature of between + 2 °C and + 30 °C, **CAF 33** can be used for up to 24 months from its date of manufacture (expiry date).

Comply with storage instructions and expiry date marked on the packaging.

Past this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety


Consult the Safety Data Sheet for **CAF 33**.

CAF® 33


Visit our website www.bluestarsilicones.com

 **EUROPE**


Bluestar Silicones France
21 Avenue Georges
Pompidou
F69486 Lyon Cedex 03
FRANCE
Tel. (33) 4 72 13 19 00
Fax (33) 4 72 13 19 88

 **NORTH AMERICA**

Bluestar Silicones USA
2 Tower Center
Boulevard
Suite 1601
East Brunswick, NJ
08816-1100
United States
Tel. (1) 732 227-2060
Fax. (1) 732 249-7000

 **LATIN AMERICA**

*Bluestar Silicones
Brazil Ltda.*
Av. Maria Coelho
Aguiar, 215
Bloco G - 1º andar
05804-902-Sao Paulo -
SP- Brazil
Tel. (55) 11 37477887

 **ASIA PACIFIC**

*Bluestar Silicones Hong
Kong
Trading Co. Ltd*
29th Floor, 88 Hing Fat
Street
Causeway Bay
Hong Kong
Tel. (852) 3106 8200
Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.