

# RHODORSIL® PRIMER 131

<b>Description</b>	<p><b>RHODORSIL PRIMER 131</b> is an adhesion promotor for Room Temperature Vulcanising silicone elastomers :</p> <ul style="list-style-type: none"> <li>- one-component (RTV-1) : CAF, RHODORSEAL,</li> <li>- two-component (RTV-2) : RHODORSIL, RTV, RHODORSEAL AXAD,</li> <li>- on a large number of surfaces.</li> </ul>
<b>Applications</b>	<p><b>RHODORSIL PRIMER 131</b> is particularly recommended for use with the following surfaces:</p> <ul style="list-style-type: none"> <li>• Aluminium.</li> <li>• Polished and unpolished stainless steel.</li> <li>• Painted, zinc plated and chrome plated steel.</li> <li>• Polar plastics: polyamide, polycarbonate, ABS.</li> </ul>
<b>Characteristics</b>	<p>Appearance ..... fluid liquid</p> <p>Colouring ..... colourless</p> <p>Specific Gravity at 25°C ..... 0.79</p> <p>Kinematic viscosity, 25°C, mm<sup>2</sup>/s, approx. .... 2.5</p> <p>Flash point (closed cup), °C, approx. .... 12 (standard AFNOR T 60103)</p> <p>Solvents ..... Isopropyl alcohol</p> <p>Diluents ..... Soluble in aliphatic hydrocarbons</p>
<b>Processing</b>	<p><b>RHODORSIL PRIMER 131</b> is particularly easy to process because it is delivered ready to use. In all cases, it must be applied to clean, dry surfaces.</p> <p><b>RHODORSIL PRIMER 131</b> is applied with a brush or dry cloth in a thin, uniform coat.</p> <p>After applying <b>RHODORSIL PRIMER 131</b> it is recommended to wait 1 or more minutes to leave it time to dry, at room temperature, before applying, pouring or injecting the silicone elastomer on the primer-prepared surface.</p> <p>In order to avoid any hydrolysis problems, it is recommended not to leave the container in contact with atmospheric humidity</p>
<b>Packaging</b>	<p><b>RHODORSIL PRIMER 131</b> is normally delivered in 800 g containers, packed 48 per outer.</p>
<b>Storage and shelf-life</b>	<p>When stored in its original unopened packaging at a temperature of between +2°C and +30 °C, <b>RHODORSIL PRIMER 131</b> can be used for up to 24 months after the date of manufacture marked on the packaging (DLU).</p> <p>Comply with storage instructions and the expiry date marked on the packaging.</p> <p>Past this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.</p>

## RHODORSIL® PRIMER 131

### Safety

Consult the Safety Data Sheet for **RHODORSIL PRIMER 131**.

Visit our website [www.bluestarsilicones.com](http://www.bluestarsilicones.com)

#### EUROPE

*Bluestar Silicones France  
21 Avenue Georges Pompidou  
F69486 Lyon Cedex 03  
FRANCE  
Tel. (33) 4 72 13 19 00  
Fax (33) 4 72 13 19 88*

#### NORTH AMERICA

*Bluestar Silicones USA  
Two Tower Center Boulevard  
Suite 1601  
East Brunswick, NJ 08816-1100  
United States  
Tel. (1) 732 227 2060  
Fax (1) 732 249 7000*

#### LATIN AMERICA

*Bluestar Silicones Brasil Ltda.  
Av. Maria Coelho Aguiar, 215, Bloco G  
-1º Andar  
05804-902 - São Paulo - SP - Brasil  
Tel. (55)-11-37477887*

#### ASIA PACIFIC

*Bluestar Silicones Hong Kong  
Trading Co., Ltd.  
29/ F, 88 Hing Fat Street  
Causeway Bay - Hong Kong  
Tel. (852) 3106 8200  
Fax (852) 2979 0241*

#### **Warning to the users**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.